

REINFORCEMENT PROTECTION BS 7



- > single component
- > plastic-tempered
- > quick setting
- > plastic-tempered

Product description

Single component, cement-bound, plastic-tempered reinforcement protection. Reinforcement Protection BS7 is very simple to process and does not need to be spread with quartz sand. Through the mineral base components and the quick setting recipe, excellent adhesion is achieved on steel and concrete.

Delivery format

Container	Outer packaging	Pallet
2 KG / KE	-	100 KE

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 365 days

Processing

Recommended tools

Slow-rotating electric mixer, brush.

Mixing

Add the complete contents of the container (2 kg) to the specified amount of water (approx. 0.44 l / 2 kg container) and mix for 3 min. with an electric agitator slowly and evenly until a uniform homogeneous and lump-free mass is created. Mix in as little air as possible.

Processing

The spreadable material is applied twice to the reinforcement rods via a brush. The second application can only take place when the first coat is load-bearing (after approx. 6 hrs.). The layer thickness must be at least 1 mm.

Technical data

Colour	grey
Consumption	approx. 0.2 kg/sqm reinforcing irons in two work steps.
Layer thickness	min. 2 mm (2 work steps)
Processing time	approx. 90 min.
Processing temperature	min. +5 °C / max. +30 °C
Water consumption	approx. 0.22 l/ kg

Test certificates

Tested in accordance with (standard, classification ...)
EN 1504-7

Substrate

Suitable substrates

Steel surfaces must be clean, hard, load-bearing and free of similar and dissimilar substances. Rust must be removed using appropriate methods (e.g. high-pressure water jets, blasting with solid blasting material). (purity of the steel after treatment: SA 2)

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The colour formation is significantly impacted by the environmental conditions.

Environmental information:

- Do not process at temperatures below +5 °C!
- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Please refer to safety data sheet for product-specific information with regard to composition, handling, cleaning, corresponding actions and disposal.

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.
- Avoid contact with the eyes and skin.

Breathing protection:

- Wear breathing protection in case of inadequate ventilation.
- Filter P2.

Hand protection:

- Protective gloves.
- The glove material must be impermeable and resistant to the product/substance/preparation.

Glove material

- Use gloves made from stable materials (e.g. nitrile).
- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: tightly sealed protective goggles.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.