Coating technology



EPOXY REINIGER EP V4



Product description

Cleaning agent for tools and equipment which are contaminated with reactive resins which have not yet

hardened.

Delivery format

Container	Outer packaging	Pallet
5 L / BKA	-	126 BKA

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 365 days

Technical data

Density approx. 0.84 g/cm³

Flashpoint +28°C

Substrate

Suitable substrates

The substrate must be dry, stable and free of separating, intrinsic and dissimilar substances, pursuant to the

IBF Directive - industrial substrates of reaction resin. Residual moisture max. 4% by weight, measured with

the CM device. Substrate temperature greater than 12 °C and 3 K above dew point; adhesive tensile strength

on average 1.5 N/mm²; adhesive tensile strength smallest single value 1.1 N/mm²

38240, EPOXY REINIGER EP V4, valid from: 09.07.2024, Nicole Zeiml, Page 1

TECHNICAL DATA SHEET

Coating technology



Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Check tinted products for colour accuracy before application!
- Colour consistency can only be guaranteed within the same batch.
- The colour formation is significantly impacted by the environmental conditions.

Environmental information:

- Do not process at temperatures below +5 °C!
- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal humidity range is 40% to 60% relative humidity.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or

temperatures will speed it up.

Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!

- Protect against direct sunlight, wind and weather!
- Protect adjacent components!

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the

indicated values of individual deliveries may vary slightly without impacting the product suitability

Safety instructions

Please refer to safety data sheet for product-specific information with regard to composition, handling, cleaning, corresponding actions and disposal.

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.
- Avoid contact with the eyes and skin.

Breathing protection:

- For short term or minor exposure use a breathing filter device; for more intensive or longer exposure use a self-contained breathing apparatus.

Hand protection: protective gloves.

Glove material

- Butyl rubber
- Nitrile rubber

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: protective goggles. Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.

38240, EPOXY REINIGER EP V4, valid from: 09.07.2024, Nicole Zeiml, Page 2