

Colour technology

SPRAY FILLER DURAPID XL 90



- > for irregular substrates
- > for efficient machine processing
- > for layer thicknesses up to approx. 5 mm

Product description

Very high filling capacity, ready-to-use organic spray filler compound for indoor machine processing. The product is ready to use. Can be processed seamlessly on large areas, especially on coarse substrates. The material remains permeable for layer thicknesses of up to approx. 5 mm and can be stropped into a level surface ready for painting or wallpapering. Indoors for filling holes and joints in wall and ceiling areas as well as for thick-layered surface fillings on uneven substrates. Layer thickness: up to approx. 5 mm per work step.

Delivery format

| Container | Outer packaging | Pallet |
|------------|-----------------|--------|
| 25 KG / KE | - | 24 KE |
| 25 KG / KS | - | 40 KS |

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 365 days

Processing

Recommended tools

Finishing spatula, airless spraying device with a nozzle size of 0.035" - 0.043" (varies depending on the device used).

Clean the tools with water immediately after use.

Processing

Spray filler Durapid XL 90 is applied via airless sprayer and smoothed with a finishing spatula. Depending on the substrate and the layer thickness desired, 1-2 work steps are required. Max. 5 mm can be applied per work step. After a drying time of approx. 48 hrs, the surface can be lightly ground or re-smoothed.

Technical data

| | |
|---------------|---------------------------------------------------------|
| Grain size | max. 0,4 mm |
| pH value | ca. 8,7 |
| Colour | white |
| Consumption | approx. 1.75 kg/m ² per 1 mm layer thickness |
| Drying time | approx. 24 hrs. |
| Flashpoint | none (does not spread or feed fire) |
| Volume weight | approx. 1.75 kg/l |

Substrate

Suitable substrates

Lime cement and cement plasters P Ic; P II; P III
Lime cement and cement plasters P II & P III
Gypsum and ready-mix plasters P IV & PV
Plasterboards and gypsum plasterboards
Concrete, aerated concrete
Exposed masonry
Weight-bearing old coats

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical national and European directives, standards and "generally accepted rules of the trade".

For a perfect system

Description

MUREXIN Deep Primer LF 14 for priming sandy and absorbent substrates.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Powdery fillers are to be used immediately after opening the original packaging.
- Do not add water to plaster fillers which have already stiffened; clean mixing vessel before mixing again.
- Pores and cavities in concrete are to be filled in a separate step, particularly to prevent the formation of bubbles in the filler.

Environmental information:

- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or higher temperatures will speed it up.
- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!
- Do not process at temperatures below 5 °C.
- Increased air humidity as a result of plaster and screed work can lead to swelling and spalling of gypsum fillers.

Tips:

50220, SPRAY FILLER DURAPID XL 90, valid from: 10.07.2024, Nicole Zeiml, Page 2

Colour technology

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.

Breathing protection: Only when spraying without sufficient extraction.

Hand protection: protective gloves.

Glove material

- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: safety goggles.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.