

FACADE ACRYLIC COLOUR RA 50

- > high coverage
- > permeable
- > high weatherproofing



Product description

Dull matt facade colour based on high quality pure silicate for carrying out more efficient permeable facade coatings. For yellowing-free and alkali-resistant facade coating as well as renovating coating both indoors and outdoors.

Delivery format

Container	Outer packaging	Pallet
20 KG / KE	-	24 KE
5 KG / KE	-	85 KE

Storage

Can be stored frost-free, cool, and dry on wooden shelves in the unopened original container for 365 days

Processing

Recommended tools

Roller, brush, airless sprayer.

Wash the tools with clean water after use.

Processing

Murexin Facade Acrylic Colour RA 50 can be applied by painting, rolling or spraying (also airless).

Usually 1-2 applications are required. For airless spraying, we recommend the following configuration: nozzle 0.026 - 0031" = 0.66 - 0.79 mm, material pressure 160 - 180 bar, spray angle 40 - 80°.

Do not process in direct, strong sunlight, rain, high humidity or strong wind.

Technical data

Chemical base
Density
Colour

Pure acrylate
ca. 1,6 kg/l
White; can be coloured with full-tone, base and shaded colours using the Murexin mixing system.

52210, FACADE ACRYLIC COLOUR RA 50, valid from: 11.07.2024, Nicole Zeiml, Page 1

Colour technology

Gloss	G3 (matt); gloss level 1.8
Consumption	per coat on fine plaster grain approx. 150 - 250 g/m ² , coarse plaster grain approx. 250 - 350 g/m ²
Dilution	Water; first coat max. 15%, dilute topcoat max. 5%
Drying time	after approx. 6 -8 hrs. surface dry and paintable Drying properties relate to 20 °C and 55% rel. humidity. Final resistance is only set after 28 days.
Water vapour diffusivity	V1 (high); 0.069 m
Waterproofing	W2 (medium); 0.12 kg/(m ² · h0.5)
Grain size	S1 (fine); < 80 µm

Test certificates

Tested in accordance with (standard, classification ...)
EN 1062-1:2004

Substrate

Suitable substrates

Lime cement and cement plasters P Ic; P II; P III
Lime cement and cement plasters P II & P III
Gypsum and ready-mix plasters P IV & PV
Plasterboards and gypsum plasterboards
Concrete, aerated concrete
Exposed masonry
Weight-bearing old coats

The substrate must be dry, frost-free, solid, weight-bearing, dimensionally stable, free of dust, dirt, oil, grease, release agents and loose parts, and it must comply with the applicable technical national and European directives, standards and "generally accepted rules of the trade".

For a perfect system

Description

Murexin Deep Primer LF 14 for priming sandy and absorbent mineral substrates.

Product and processing instructions

Material information:

- If processing outside the ideal temperature and/or humidity range the material properties could change markedly.
- Bring the materials to the proper temperature before processing!
- In order to maintain the product properties, do not add any foreign materials!
- Water dosing quantities or dilution information must be strictly adhered to!
- Carefully open the container, remove possible dry parts and shake the product well!
- Water-based systems have only a limited shelf life after dilution with water, which is why quick processing is recommended.

Environmental information:

- The ideal temperature range for the material, substrate and air is + 15 °C to + 25 °C.
- The ideal relative humidity range is 40% to 60%.
- Increased air humidity and/or lower temperatures may prolong the drying, setting and hardening time, while lower air humidity and/or

52210, FACADE ACRYLIC COLOUR RA 50, valid from: 11.07.2024, Nicole Zeiml, Page 2

Colour technology

higher temperatures will speed it up.

- Ensure adequate ventilation during the drying, reaction and hardening phase; avoid draughts!
- Protect against direct sunlight, wind and weather!
- Protect adjacent components!
- Do not process at temperatures below 5 °C.

Tips:

- We recommend using a test surface first or a small area for initial, small-scale testing.
- Please heed the product data sheets of all MUREXIN products used in the process.
- Keep a genuine original container of the respective batch for later repair work.
- When using intensive, brilliant and dark colours, we recommend using the colour qualities of wet abrasion class ≤ 2 in at least "satin finish" (gloss level $>15/60^\circ$ MW) and first equalising the substrate in "white".
- In case of side lighting, we recommend using colour qualities of wet abrasion class ≤ 2 in "dull matt" (gloss level $<5/85^\circ$ MW).

The information provided reflects average values that were obtained under laboratory conditions. Due to the use of natural raw materials, the indicated values of individual deliveries may vary slightly without impacting the product suitability.

Safety instructions

Limiting and monitoring exposure

Personal protective equipment:

General protection and hygiene measures:

- Common safety measures for handling chemicals are to be observed.
- Keep away from foodstuffs, beverages and feedstuffs.
- Take off contaminated, impregnated clothing immediately.
- Wash your hands before taking breaks and when finishing work.

Breathing protection: not required.

Hand protection: protective gloves.

Glove material

- Use gloves made from stable materials (e.g. nitrile).
- The selection of a suitable glove depends not only on the material, but also on other quality properties, which may vary from manufacturer to manufacturer.

Penetration time of the glove material

- The precise penetration time is to be found out from the protective glove manufacturer and complied with.

Eye protection: Protective goggles recommended when decanting.

Body protection: protective clothing.

This leaflet is based on extensive experience, is intended to convey the best of our knowledge, is not legally binding and does neither constitute a contractual legal relationship nor a subsidiary obligation resulting from the bill of sale. The quality of our materials is guaranteed within the framework of our general terms and conditions. Our products may be used by professionals and/or experienced and accordingly technically skilled persons only. Users are not released from inquiring in case of uncertainties or from rendering professional workmanship. We recommend using a test surface first or a small area for initial, small-scale testing. Naturally, it is not possible to describe or foresee all possible current and future uses and peculiarities. Information that is assumed to be familiar to experts has been omitted.

Please observe the current, technical, national and European standards, guidelines and data sheets regarding materials, substrates and the subsequent construction. Please contact us if you have any reservations or doubt.

This version is rendered invalid if a new version is released. The most recent data sheets, safety data sheets and the terms and conditions are available online at www.murexin.com.